IN THE CLAIMS:

1. (currently amended) An airlaid composite absorbent web comprising a homogenous mixture of binder and particles of coated superabsorbent and wherein the particles of coated superabsorbent material comprise above about 75 to about 98 weight percent of the airlaid composite and the binder comprises from below about 25 to about 2 weight percent of the airlaid composite.

2. (original) The airlaid composite absorbent web according to Claim 1 wherein the particles of coated superabsorbent material comprise from about 30% to about 97% superabsorbent material and from about 70% to about 3% cellulose fiber or other materials.

3. (cancelled)

- 4. (original) The airlaid composite absorbent web according to Claim 1 wherein the binder comprises less than about 20 weight percent of the web.
- 5. (original) The airlaid composite absorbent web according to Claim 1 wherein the binder comprises less than about 10 weight percent of the web.

KCC-1162 2 RWN/pc

6. (currently amended) The airlaid composite absorbent web according to Claim 3-1 wherein the binder is a thermoplastic fiber.

- 7. (original) The airlaid composite absorbent web according to Claim 6 wherein the thermoplastic fibers are bicomponent fibers.
- 8. (original) The airlaid composite absorbent web according to Claim 6 wherein the thermoplastic fibers are PE/PET staple fibers.
- 9. (currently amended) The airlaid composite absorbent web according to Claim 3-1 wherein the binder comprises meltblown fibers.
- 10. (original) The airlaid composite absorbent web according to Claim 1 wherein the binder comprises elastomeric fibers.
- 11. (original) The airlaid composite absorbent web according to Claim 10 wherein the elastomeric fibers comprise a polymer selected from the group including styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene block copolymers, styrene-ethylene/butylene-styrene block copolymers, styrene-ethylene/-propylene-styrene block copolymers, polyurethanes, elastomeric polyamides, elastomeric polyesters, elastomeric polyolefin homopolymers and copolymers, atactic polypropylenes, ethylene vinyl acetate

KCC-1162 3 RWN/pc

copolymers, single-site or metallocene catalyzed polyolefins having a density less than about 0.89 grams/cc, and combinations thereof.

- 12. (original) The airlaid composite absorbent web according to Claim 1 wherein the absorbent composite web is between about 50 gsm and about 1500 gsm basis weight.
- 13. (currently amended) The airlaid composite absorbent web according to Claim 1 wherein the absorbent composite web comprises greater than or equal to about 2 weight percent thermoplastic binder fiber and less than or equal to about ninety eight weight percent particles of coated superabsorbent.
- 14. (currently amended) The airlaid composite absorbent web according to Claim 13-1 further comprising between about 30 weight percent and above about 85 weight percent coated superabsorbent material.
- 15. (original) The airlaid composite absorbent web according to Claim 1 further comprising at least one of non-coated superabsorbent materials, pulp fibers, synthetic fibers, odor control agents, and other natural or synthetic materials.

KCC-1162 4 RWN/pc

16. (original) The airlaid composite absorbent web according to Claim 1 wherein the absorbent composite web has an absorbent capacity of between about 15 g/g and about 40 g/g.

- 17. (original) The airlaid composite absorbent web according to Claim 1 wherein the composite absorbent web has a density of between about 0.1 g/cc and about 0.5 g/cc.
- 18. (currently amended) An airlaid composite absorbent web comprising a homogenous mixture of binder and particles of cellulose-coated superabsorbent and wherein the particles of cellulose-coated superabsorbent material comprise above about 75 to about 98 weight percent of the airlaid composite and the binder comprises from below about 25 to about 2 weight percent of the airlaid composite.
- 19. (original) The airlaid composite absorbent web according to Claim 18 wherein the particles of cellulose-coated superabsorbent material comprise from about 30% to about 97% superabsorbent material and from about 70% to about 3% cellulose fiber.

20. (cancelled)

21. (original) The airlaid composite absorbent web according to Claim 18 wherein the binder comprises less than about 20 weight percent of the web.

KCC-1162 5 RWN/pc

22. (original) The airlaid composite absorbent web according to Claim 18 wherein the binder comprises less than about 10 weight percent of the web.

- 23. (original) The airlaid composite absorbent web according to Claim 20 wherein the binder comprises thermoplastic fibers.
- 24. (original) The airlaid composite absorbent web according to Claim 23 wherein the thermoplastic fibers are bicomponent fibers.
- 25. (original) The airlaid composite absorbent web according to Claim 23 wherein the thermoplastic fibers are PE/PET staple fibers.
- 26. (currently amended) The airlaid composite absorbent web according to Claim-20 18 wherein the binder comprises meltblown fibers.
- 27. (original) The airlaid composite absorbent web according to Claim 18 wherein the binder comprises elastomeric fibers.
- 28. (original) The airlaid composite absorbent web according to Claim 27 wherein the elastomeric fibers comprise a polymer selected from the group including styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene block copolymers, styrene-

KCC-1162 6 RWN/pc

ethylene/butylene-styrene block copolymers, styrene-ethylene/-propylene-styrene block copolymers, polyurethanes, elastomeric polyamides, elastomeric polyesters, elastomeric polyolefin homopolymers and copolymers, atactic polypropylenes, ethylene vinyl acetate copolymers, single-site or metallocene catalyzed polyolefins having a density less than about 0.89 grams/cc, and combinations thereof.

- 29. (original) The airlaid composite absorbent web according to Claim 18 wherein the absorbent composite web is between about 50 gsm and about 1500 gsm basis weight.
- 30. (currently amended) The airlaid composite absorbent web according to Claim 18 wherein the absorbent composite web comprises greater than or equal to about 2 weight percent thermoplastic binder fiber and less than or equal to about ninety eight weight percent particles of coated superabsorbent.
- 31. (currently amended) The airlaid composite absorbent web according to Claim 30 further comprising between about 30 weight percent and above about 85 weight percent coated superabsorbent material.
- 32. (original) The airlaid composite absorbent web according to Claim 18 further comprising at least one of non-coated superabsorbent materials, pulp fibers, synthetic fibers, odor control agents, and other natural or synthetic materials.

KCC-1162 7 RWN/pc

33. (original) The airlaid composite absorbent web according to Claim 18 wherein the absorbent composite web has an absorbent capacity of between about 15 g/g and about 40 g/g.

- 34. (original) The airlaid composite absorbent web according to Claim 18 wherein the composite absorbent web has a density of between about 0.1 g/cc and about 0.5 g/cc.
- 35. (original) An airlaid composite absorbent web consisting essentially of a homogenous mixture of binder and particles of coated superabsorbent.
- 36. (original) The airlaid composite absorbent web according to Claim 35 wherein the particles of coated superabsorbent material comprise from about 30% to about 97% superabsorbent material and from about 70% to about 3% cellulose fiber.
- 37. (original) The airlaid composite absorbent web according to Claim 35 wherein the binder comprises less than about 40 weight percent of the web.
- 38. (currently amended) The airlaid composite absorbent web according to Claim 35 wherein the binder matrial comprises less than about 20 weight percent of the web.

KCC-1162 8 RWN/pc

39. (original) The airlaid composite absorbent web according to Claim 35 wherein the binder comprises less than about 10 weight percent of the web.

- 40. (original) The airlaid composite absorbent web according to Claim 37 wherein the binder comprises thermoplastic fibers.
- 41. (original) The airlaid composite absorbent web according to Claim 40 wherein the thermoplastic fibers are bicomponent fibers.
- 42. (original) The airlaid composite absorbent web according to Claim 40 wherein the thermoplastic fibers are PE/PET staple fibers.
- 43. (original) The airlaid composite absorbent web according to Claim 37 wherein the binder comprises meltblown fibers.
- 44. (original) The airlaid composite absorbent web according to Claim 35 wherein the binder comprises elastomeric fibers.
- 45. (original) The airlaid composite absorbent web according to Claim 44 wherein the elastomeric fibers comprise a polymer selected from the group including styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene block copolymers, styrene-

KCC-1162 9 RWN/pc

ethylene/butylene-styrene block copolymers, styrene-ethylene/-propylene-styrene block copolymers, polyurethanes, elastomeric polyamides, elastomeric polyesters, elastomeric polyolefin homopolymers and copolymers, atactic polypropylenes, ethylene vinyl acetate copolymers, single-site or metallocene catalyzed polyolefins having a density less than about 0.89 grams/cc, and combinations thereof.

- 46. (original) The airlaid composite absorbent web according to Claim 35 wherein the absorbent composite web is between about 50 gsm and about 1500 gsm basis weight.
- 47. (currently amended) The airlaid composite absorbent web according to Claim 35 wherein the absorbent composite web emprises-consists essentially of greater than or equal to about 2 weight percent thermoplastic binder fiber and less than or equal to about ninety eight weight percent particles of cellulose-coated superabsorbent.
- 48. (currently amended) The airlaid composite absorbent web according to Claim 35 further <u>comprising consisting essentially of between about 30 weight percent and about 85 weight percent cellulose-coated superabsorbent material.</u>
- 49. (currently amended) The airlaid composite absorbent web according to Claim 35 further comprising consisting essentially of at least one of non-coated

KCC-1162 10 RWN/pc

superabsorbent materials, pulp fibers, synthetic fibers, odor control agents, and other natural or synthetic materials.

- 50. (original) The airlaid composite absorbent web according to Claim 35 wherein the absorbent composite web has an absorbent capacity of between about 15 g/g and about 40 g/g.
- 51. (original) The airlaid composite absorbent web according to Claim 35 wherein the composite absorbent web has a density of between about 0.1 g/cc and about 0.5 g/cc.
- 52. (original) An airlaid composite absorbent web consisting essentially of a homogenous mixture of binder and particles of cellulose-coated superabsorbent.
- 53. (original) The airlaid composite absorbent web according to Claim 52 wherein the particles of cellulose-coated superabsorbent material comprise from about 30% to about 97% superabsorbent material and from about 70% to about 3% cellulose fiber.
- 54. (original) The airlaid composite absorbent web according to Claim 52 wherein the binder comprises less than about 40 weight percent of the web.

KCC-1162 11 RWN/pc

55. (original) The airlaid composite absorbent web according to Claim 52 wherein the binder comprises less than about 20 weight percent of the web.

- 56. (original) The airlaid composite absorbent web according to Claim 52 wherein the binder comprises less than about 10 weight percent of the web.
- 57. (original) The airlaid composite absorbent web according to Claim 54 wherein the binder comprises thermoplastic fibers.
- 58. (original) The airlaid composite absorbent web according to Claim 57 wherein the thermoplastic fibers are bicomponent fibers.
- 59. (original) The airlaid composite absorbent web according to Claim 57 wherein the thermoplastic fibers are PE/PET staple fibers.
- 60. (original) The airlaid composite absorbent web according to Claim 54 wherein the binder comprises meltblown fibers.
- 61. (original) The airlaid composite absorbent web according to Claim 52 wherein the binder comprises elastomeric fibers.

KCC-1162 12 RWN/pc

62. (original) The airlaid composite absorbent web according to Claim 61 wherein the elastomeric fibers comprise a polymer selected from the group including styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene block copolymers, styrene-ethylene/butylene-styrene block copolymers, styrene-ethylene/-propylene-styrene block copolymers, polyurethanes, elastomeric polyamides, elastomeric polyesters, elastomeric polyolefin homopolymers and copolymers, atactic polypropylenes, ethylene vinyl acetate copolymers, single-site or metallocene catalyzed polyolefins having a density less than about 0.89 grams/cc, and combinations thereof.

- 63. (original) The airlaid composite absorbent web according to Claim 52 wherein the absorbent composite web is between about 50 gsm and about 1500 gsm basis weight.
- 64. (currently amended) The airlaid composite absorbent web according to Claim 52 wherein the absorbent composite web emprises consists essentially of greater than or equal to about 2 weight percent thermoplastic binder fiber and less than or equal to about ninety eight weight percent particles of cellulose-coated superabsorbent.
- 65. (currently amended) The airlaid composite absorbent web according to Claim 64 further comprising consisting essentially of between about 30 weight percent and about 85 weight percent cellulose-coated superabsorbent material.

KCC-1162 13 RWN/pc

66. (currently amended) The airlaid composite absorbent web according to Claim 52 further consists essentially of comprising—at least one of non-coated superabsorbent materials, pulp fibers, synthetic fibers, odor control agents, and other natural or synthetic materials.

- 67. (original) The airlaid composite absorbent web according to Claim 52 wherein the absorbent composite web has an absorbent capacity of between about 15 g/g and about 40 g/g.
- 68. (original) The airlaid composite absorbent web according to Claim 52 wherein the composite absorbent web has a density of between about 0.1 g/cc and about 0.5 g/cc.
- 69. (original) The airlaid composite absorbent web according to Claim 1 wherein the absorbent composite web further comprises a support member.
- 70. (original) The airlaid composite absorbent web according to Claim 69 wherein the support member comprises at least one of a spunbond web, a meltblown web, a nonwoven web, a tissue web or a pulp web.
- 71. (original) The airlaid composite absorbent web according to Claim 18 wherein the absorbent composite web further comprises a support member.

KCC-1162 14 RWN/pc

72. (original) The airlaid composite absorbent web according to Claim 71 wherein the support member comprises at least one of a spunbond web, a meltblown web, a nonwoven web, a tissue web or a pulp web.

73. (currently amended) The airlaid composite absorbent web according to Claim 35 wherein the absorbent composite web further comprises consists essentially of a support member.

74. (original) The airlaid composite absorbent web according to Claim 73 wherein the support member comprises at least one of a spunbond web, a meltblown web, a nonwoven web, a tissue web or a pulp web.

75. (currently amended) The airlaid composite absorbent web according to Claim 52 wherein the absorbent composite web further comprises consists essentially of a support member.

76. (original) The airlaid composite absorbent web according to Claim 75 wherein the support member comprises at least one of a spunbond web, a meltblown web, a nonwoven web, a tissue web or a pulp web.

KCC-1162 15 RWN/pc

77. (new) The airlaid composite absorbent web according to Claim 1 wherein the absorbent composite web has an edge compression of below about 1.2 g/gsm.

- 78. (new) The airlaid composite absorbent web according to Claim 77 wherein the absorbent composite web has a saturated capacity of above about 18 g/g.
- 79. (new) The airlaid composite absorbent web according to Claim 78 wherein the absorbent composite web has a wet tensile strength of greater than about 0.5 g/gsm/in.
- 80. (new) The airlaid composite absorbent web according to Claim 18 wherein the absorbent composite web has an edge compression of below about 1.2 g/gsm.
- 81. (new) The airlaid composite absorbent web according to Claim 80 wherein the absorbent composite web has a saturated capacity of above about 18 g/g.
- 82. (new) The airlaid composite absorbent web according to Claim 81 wherein the absorbent composite web has a wet tensile strength of greater than about 0.5 g/gsm/in.
- 83. (new) The airlaid composite absorbent web according to Claim 35 wherein the absorbent composite web has an edge compression of below about 1.2 g/gsm.

KCC-1162 16 RWN/pc

84. (new) The airlaid composite absorbent web according to Claim 83 wherein the absorbent composite web has a saturated capacity of above about 18 g/g.

- 85. (new) The airlaid composite absorbent web according to Claim 84 wherein the absorbent composite web has a wet tensile strength of greater than about 0.5 g/gsm/in.
- 86. (new) The airlaid composite absorbent web according to Claim 52 wherein the absorbent composite web has an edge compression of below about 1.2 g/gsm.
- 87. (new) The airlaid composite absorbent web according to Claim 86 wherein the absorbent composite web has a saturated capacity of above about 18 g/g.
- 88. (new) The airlaid composite absorbent web according to Claim 87 wherein the absorbent composite web has a wet tensile strength of greater than about 0.5 g/gsm/in.